

**MiyoAQUA Natural Loose Powder**

**ULP0001**

A simplified formula for a smooth, silky, loose powder with natural coverage

Phase	Trade Name	INCI Name	Function	Supplier	%
A	NAI-S-100	Sericite (and) Disodium Stearoyl Glutamate		Miyoshi America, Inc.	37.75%
	MiyoAQUA Black NH	Iron Oxides (and) Algin			0.19%
	MiyoAQUA Red	Iron Oxides (and) Algin			0.33%
	MiyoAqua Yellow	Iron Oxides (and) Algin			0.99%
	Sericite CS-15	Mica			37.74%
	Boron Nitride	Boron Nitride		GE Advanced Materials	6.00%
	Ronafclair® ESQ	Bismuth Oxychloride		EMD Performance Materials	12.00%
B	Euxyl K-712	Water (and) Sodium Benzoate (and) Potassium Sorbate		Schulke	1.00%
	Fitoderm®	Squalane		BASF Care Creations	4.00%

Procedure	
1	Warm Phase B to about 50°C
2	Pre-mix Phase A in a blender for 1.5 minutes on high speed.
3	Add Phase B to Phase A and mix on high speed for 1.5 minutes. Package into desired containers.